

SmartPly OSB3

SmartPly OSB3 is a highly engineered, moisture resistant load-bearing panel designed for use in humid conditions and is therefore ideal for many structural and non-structural applications in both internal and protected external environments. Manufactured in accordance with EN 300 performance standard, it is the perfect choice for roofing, flooring, wall sheathing, site hoarding and many other applications where strength and moisture resistance are paramount.



Quality and Environmental Certification:

SmartPly OSB is manufactured in accordance with the requirements of EN 300: *Oriented Strand Boards (OSB) – definitions, classification and specifications*.

SmartPly OSB is CE marked in accordance with the harmonised standard EN 13986: *Wood-based panels for use in construction – characteristics, evaluation of conformity and marking*. This standard is a technical specification for wood-based panels which implements the provisions of the Construction Products Regulation (CPR) formerly the Construction Products Directive (CPD). In addition to the CE mark, SmartPly OSB panels are marked 2+ Structural for ease of reference.

SmartPly OSB3 is certified by the British Board of Agrément (BBA) and the Irish Agrément Board (IAB). Due to this certification it is permitted for structural use by NHBC (UK) and Homebond (Ireland) when used in accordance with the requirements of the Building Regulations in the country of

use. Other quality certification includes SINTEF (Norway) and KOMO (Netherlands).

SmartPly has achieved I.S. EN ISO 9001:2008, the internationally recognised quality management system which is certified by the National Standards Authority of Ireland (NSAI).

SmartPly has Forest Stewardship Council (FSC) Chain of Custody certification for its manufacturing, processing, sales and distribution processes.

SmartPly operates under an Integrated Pollution Prevention Control (IPPC) licence, which is monitored by the Environmental Protection Agency (EPA) in Ireland.

All SmartPly OSB3 products are manufactured using formaldehyde-free resin.

Suitability: EN 300 classifies OSB panels by their properties which relate to their intended use. SmartPly OSB3 is classified as a load-bearing panel for use in humid conditions.

Structures comprising SmartPly OSB3 should be assigned to service class 1 or 2 as defined in EN 1995-1-1 (Eurocode 5). According to this standard, SmartPly OSB3 is suitable for use in both of these service classes.

Moisture conditions can affect the performance of wood-based panels. Therefore, it is important that the correct type of OSB is specified for a particular service class. Always check current regulations specific to the country of use.

As well as conditions in service, consideration must also be given to the construction phase where high levels of moisture or humidity often exist. Consideration should also be given to end-use applications that may be at risk of short-term wetting, such as from burst water pipes or leaking appliances. In such conditions SmartPly strongly recommends the use of OSB3.

According to EN 300, SmartPly OSB3 is suitable for use in Use classes 1 and 2 of EN 335. Furthermore, SmartPly's innovative OSB3 SiteProtect (coated hoarding panel) is suitable for use in Use class 3 of EN 335.

Specification and design: As design values can vary between manufacturers, it is important to ensure that the SmartPly OSB3 panels specified by the designer are those used on site. All SmartPly panels are clearly marked with the following information:

- (a) Major axis (length of panel, direction of laying arrows)
- (b) Production identification number
- (c) Product Certification mark (e.g. BBA, IAB)
- (d) CE marking
 - i. Manufacturer's name / Logo (SmartPly)
 - ii. Notified body identification number
 - iii. Quality standard (EN 300, EN 13986)
 - iv. Panel type (e.g. OSB3)
 - v. Thickness (e.g. 18mm)
 - vi. Formaldehyde class (e.g. E1)
- (e) Additional marking for ease of reference (e.g. 2+ structural)
- (f) FSC certification

Note: Markings may vary depending on product type.

SmartPly OSB3 - Zero added formaldehyde:

SmartPly OSB3 is manufactured using advanced resin technology that results in a high performance, zero added formaldehyde panel that scores highly in 'The Green Guide to Specification' (see below).

This specialist resin formulation provides a supreme bond with the wood strands as it has a reaction with the wood itself, when put under intense heat, creating a chemical weld. This is a different and superior type of bond to the mechanical weld that formaldehyde-based products exhibit. Depth of penetration is well beyond the minimum 0.3 mm needed for a wood resin to provide adequate adhesive strength. This extra resin penetration also greatly improves the wood's resistance to thickness swell.

SmartPly OSB3 and 'The Green Guide to Specification':

'The Green Guide to Specification' provides designers and specifiers with robust information to assist decision-making by translating numerical life cycle assessment data into simple A+ to E scale of environmental ratings, enabling specifiers to make the best environmental choices when selecting construction materials and components.

Since 1998, The Green Guide has formed part of the BRE Environmental Assessment Method (BREEAM), EcoHomes and more recently The Code For Sustainable Homes, becoming a leading construction-embodied impact assessment tool.

Specifiers using The Green Guide will be aware that OSB3, of which SmartPly is a market leading supplier, consistently scores well for overall environmental impact. Numerous examples are given in the guide where OSB3 contributes to an overall summary rating for elements of A and A+ and as a result consistently score better than those same elements in which plywood is specified.

SmartPly OSB3 has been independently assessed and meets the BREEAM requirement relevant to formaldehyde testing and therefore under section 'Hea 9 – Volatile Organic Compounds' can be awarded the maximum available 1 credit.

A Guide published by Greenpeace in August 2008, titled: 'Setting a New Standard: Alternatives to unsustainable plywood in the UK construction industry', has cited FSC certified Oriented Strand Board (OSB), of which SmartPly is a market leading supplier, as one of the most environmentally sound alternatives to non-FSC certified plywood for all manner of building projects.

Table 1 Mechanical and physical properties of SmartPly OSB3

Mechanical properties	Test method	Unit	Requirement		
Panel thickness	–	mm	6-10	11-17	18-25
Density	EN 323	kg/m ³	≥ 600	≥ 600	≥ 600
Mean density tolerance	EN 323	%	+/- 15	+/- 15	+/- 15
Bending strength (MOR) - major axis	EN 310	N/mm ²	≥ 22	≥ 20	≥ 18
Bending strength (MOR) - minor axis	EN 310	N/mm ²	≥ 11	≥ 10	≥ 9
Modulus of elasticity (MOE) - major axis	EN 310	N/mm ²	≥ 3500	≥ 3500	≥ 3500
Modulus of elasticity (MOE) - minor axis	EN 310	N/mm ²	≥ 1400	≥ 1400	≥ 1400
Internal bond	EN 319	N/mm ²	≥ 0.34	≥ 0.32	≥ 0.30
Internal bond after boil test	EN 1087-1	N/mm ²	≥ 0.15	≥ 0.13	≥ 0.12
Swelling in thickness 24h	EN 317	%	≤ 15	≤ 15	≤ 15
Formaldehyde release - perforator value	EN 120	mg/100g	≤ 8.0 (E1)	≤ 8.0 (E1)	≤ 8.0 (E1)
Moisture content - ex works	EN 322	%	2-12	2-12	2-12
General tolerances	Test Method	Unit	Requirement		
Length	EN 324-1	mm	+/- 3.0	+/- 3.0	+/- 3.0
Width	EN 324-1	mm	+/- 3.0	+/- 3.0	+/- 3.0
Thickness (un-sanded)	EN 324-1	mm	+/- 0.8	+/- 0.8	+/- 0.8
Thickness (sanded)	EN 324-1	mm	+/- 0.3	+/- 0.3	+/- 0.3
Edge straightness	EN 324-2	mm/m	+/- 1.5	+/- 1.5	+/- 1.5
Squareness	EN 324-2	mm/m	≤ 2.0	≤ 2.0	≤ 2.0
Building physics calculation values	Test Method / Reference standard	Unit	Calculation value		
Water vapour resistance factor (μ-value)	EN 12524 EN 13986	–	30 (wet cup μ) / 50 (dry cup μ)		
Reaction to fire (BS)	BS 476-7 AD B 2006	–	Class 3		
Reaction to fire (Euroclass)	EN 13501-1 EN 13986	–	(≥ 9 mm) D-s1,d0 (excluding floorings) (≥ 9 mm) DFL-s1 (floorings)		
Charring rate (β ₀ ,ρ,t)	EN 1995-1-2	mm/min	(≥ 20 mm) 0.78		
Thermal conductivity (λ)	EN 13986	W/(m.K)	0.13		
Airborne sound insulation	EN 13986	dB	R = 13 x lg (m _A) + 14 : (1-3 kHz at m _A >5 kg/m ²)		
Sound absorption coefficients	EN 13986	–	0.10 (frequency range 250 Hz to 500 Hz) 0.25 (frequency range 1000 Hz to 2000 Hz)		
Dimensional change at 1% change in panel moisture content	EN 318 DD CEN/TS 12872	%	Length 0.02	Width 0.03	Thickness 0.5

Structural design of SmartPly OSB3:

BS 8103-3 provides “deemed to satisfy” tables and other structural design guidance to enable supervisory/ technical staff of building companies to determine the thickness, type and any limitations of OSB components for floors and roofs of dwellings of limited size. A structural engineer should be employed where the building falls outside the scope of this part of BS 8103. Further technical guidance is provided in the relevant SmartPly product technical data sheets.

Characteristic values for strength and stiffness of OSB3 are given in Table 2 (below). These can be used for limit state designs to EN 1995-1-1 (Eurocode 5). For permissible stress designs to BS 5268, conversion factors are given in BS 5268-2 to convert these characteristic strength and stiffness values into grade strength and

stiffness values. The properties listed include bending, tension, compression and shear.

When OSB3 is used structurally under service class 1 conditions, the characteristic values of the mechanical properties given in Table 1 shall apply. To convert these values into design values they should be modified according to EN 1995-1-1 (Eurocode 5) for duration of load (k_{mod} , k_{def}).

When OSB3 is used structurally under service class 2 conditions, the characteristic values of the mechanical properties given in Table 1 shall apply. To convert these values into design values they should be modified according to EN 1995-1-1 (Eurocode 5) for both service class and duration of load (k_{mod} , k_{def}).

Table 2 Characteristic values for strength and stiffness of OSB3:		Taken from BS EN 12369-1		
Property	Designation	Thickness range (mm)		
		>6 - 10	>10 – 18	>18 - 25
Characteristic Strength Properties (N/mm²)				
Bending strength				
Parallel to span	$f_{m,0,k}$	18	16.4	14.8
Perpendicular to span	$f_{m,90,k}$	9.0	8.2	7.4
Tensile strength				
Parallel to span	$f_{t,0,k}$	9.9	9.4	9.0
Perpendicular to span	$f_{t,90,k}$	7.2	7.0	6.8
Compressive strength				
Parallel to span	$f_{c,0,k}$	15.9	15.4	14.8
Perpendicular to span	$f_{c,90,k}$	12.9	12.7	12.4
Shear strength				
Panel (as a racking panel)	$f_{v,k}$	6.8	6.8	6.8
Planar (as in floor decking)	$f_{v,r,k}$	1.0	1.0	1.0
Stiffness Properties (N/mm²)				
Modulus of elasticity				
Mean, in bending parallel to span	$E_{0,mean}$	4930	4930	4930
Mean, in bending perpendicular to span	$E_{90,mean}$	1980	1980	1980
Mean, in tension and compression parallel to span	$E_{ct,0,mean}$	3800	3800	3800
Mean, in tension and compression perpendicular to span	$E_{ct,90,mean}$	3000	3000	3000
Shear modulus				
Panel (as in a racking panel)	$G_{v,mean}$	1080	1080	1080
Planar (as in floor decking)	$G_{r,mean}$	50	50	50
Notes:				
<ul style="list-style-type: none"> $0 =$ in the direction of the major axis. $90 =$ in the direction of the minor axis. These properties relate to an equilibrium moisture content of the test pieces conditioned at a temperature of 20°C and a relative humidity of 65%. The 5th percentile characteristic values for stiffness should be taken as 0.85 x the mean values given in the table. 				

Important Notes: The recommendations provided in this technical data sheet for the correct use of SmartPly OSB3 are specifically designed to ensure longevity and performance of this quality product in service. It is therefore essential that these recommendations are strictly followed. The product is designed to be installed by a competent general builder or contractor, experienced with this type of product, in strict accordance with the technical guidance provided in the relevant SmartPly product technical data sheets. SmartPly Europe Ltd cannot be held responsible for damages arising from non-adherence to these recommendations, or product failures resulting from inadequate structural design or misuse of this product.

In order to provide comprehensive guidance for the correct use of SmartPly OSB3, this technical datasheet makes reference to relevant BS and EN standards. SmartPly Europe Ltd cannot be held responsible for claims arising from the use of any information that has been extracted from such sources.

For further information and/ or technical advice please contact your local SmartPly Sales Representative or SmartPly Technical Support Personnel through any of our European offices.

- +44 (0) 1322 424900
- +31 (0) 475 399740
- + 353 (0) 51 832700

As we continually update our technical datasheets, please check on www.smartply.com that you have the latest version. V 09/12



SmartPly[®]
The Smart OSB Answer to Plywood